

Glass-Glass-Module: Vision 60M high power

#### **SOLARWATT Solar Modules**

# THE INNOVATIVE GLASS-GLASS GENERATION **VISION 60M HIGH POWER**

- Super lightweight thanks to glass just 2 mm thick
- Exceptionally reliable yield rates
- 100 % protection against PID
- Increased fire protection
- Monocrystalline high power solar cells
- 295 Wp 305 Wp (100 % plus sorting)

# **Product Quality**

- long-lasting
- resilient
- high-yield
- innovative
- safe

- low-glare
- · resistant against ammonia
- resistant against hail
- resistant against salt mist











#### **SOLARWATT Service**



**SOLARWATT Full Coverage** included (up to 1000 kWp\*)



Take-back service as per "Delivery Terms for SOLARWATT Solar Modules"



**Product-warranty** 

as per "Special Warranty Conditions for SOLARWATT Solar Modules"



Performance-warranty

as per "Special Warranty Conditions for SOLARWATT Solar Modules"




**Country of origin** Quality made in Germany


#### Technical Data | Vision 60M high power

#### . 31



## **DIMENSIONS**





# **ELECTRICAL DATA (STC)**

STC: Standard Test Conditions: Irradiation intensity 1000 W/m², spectral distribution AM 1,5 | Temperature 25±2 °C, in accordance to EN 60904-3

Nominal power P <sub>N</sub>	295 Wp	300 Wp	305 Wp
Nominal voltage U <sub>MPP</sub>	31,7 V	31,9 V	32,1 V
Nominal current I <sub>MPP</sub>	9,40 A	9,50 A	9,60 A
Open circuit voltage U <sub>oc</sub>	39,6 V	39,8 V	40,0 V
Short circuit current I <sub>sc</sub>	9,85 A	9,97 A	10,09 A

Measurement tolerance in reference to Pmax ±5 %;


Reduction of module efficiency when irradiance is reduced from  $1000 \text{ W/m}^2$  to  $200 \text{ W/m}^2$  (at  $25^{\circ}\text{C}$ ):  $4 \pm 2^{\circ}\text{C}$  (relative)  $I = 0.05 \pm 0.03$  % (absolute). Reverse-current power rating  $I_0$ :  $20^{\circ}\text{A}$ , operating modules with an external power source is only permissible if using a phase fuse with a tripping current of  $I = 0.05 \pm 0.03$  % (absolute).

# **GENERAL DATA**

Module technology	Glass-Glass Laminate; aluminum frame, black anodized	
Covering material Encapsulation Backing material	Tempered solar glass with anti-reflective finish, 2 mm EVA-solar cells-EVA, white Solar glass, 2 mm	
Solar cells	60 monocrystalline high power solar cells	
Cell dimensions	156 x 156 mm	
L x W x H / Weight	1680 <sup>± 2</sup> x 990 <sup>± 2</sup> x 40 <sup>± 0,3</sup> mm / appr. 22,8 kg	
Connection technology	Cables 2 x 1,0 m/4 mm², Hirschmann HC4-connector	
Bypass diodes	3	
Application class	A (acc. to IEC 61730)	
Max. system voltage	1000 V	
Mechanical Ratings as per IEC 61215 Ed.2	Suction load up to 2400 Pa Applied load up to 5400 Pa	
Approved stress load as per SOLARWATT Installation Instructions	Applied load up to 3500 Pa (when installed crosswise <sup>1</sup> ) Test condition: sliding load of 5400 Pa (conditions take into account safety factors for snow overhang and ice load per Eurocode 1.)  1) Please refer to the specifications in the installation instructions.	
Qualifications	IEC 61215 Ed.2   IEC 61730 (including Protection Class II)	

# CHARACTERISTIC LINES (Performance Class 300 Wp)

Voltage characteristic line at different temperatures and irradiations



## **ELECTRICAL DATA (NOCT)**

NOCT: Normal Operation Cell Temperature: Irradiation intensity 800 W/m², AM 1,5 | Temperature 20°C, Wind speed 1m/s, open circuit operation

Nominal power P <sub>N</sub>	218 W	221 W	225 W
Nominal voltage U <sub>MPP</sub>	29,2 V	29,4 V	29,6 V
Open circuit voltage U <sub>oc</sub>	37,1 V	37,3 V	37,5 V
Short circuit current I <sub>sc</sub>	7,96 A	8,06 A	8,15 A

#### THERMAL FEATURES

Operating temperature range	-40 +85 °C	
Ambient temperature range	-40 +45 °C	
Temperature coefficient P <sub>N</sub>	-0,39%/K	
Temperature coefficient U <sub>oc</sub>	-0,31%/K	
Temperature coefficient I <sub>sc</sub>	0,05 %/K	
NOCT	45°C	